

Glenwood White 762 x WP699


Register no: JW1268

25 months old Merino ram

DENSITY:		LENGTH: 171 days wool growth	
Mean fibre diameter (microns)	15.3	Crimps per cm	3.5
Secondary follicle to primary follicle ratio	34.7	Fibre growth rate (mm per day)	0.36
Follicle density (per mm ²)	76.8	Fibre length to staple length ratio	1.38
SKIN THICKNESS (mm compressed):	0.52	CYLINDRICAL FIBRES (%):	

DIAMETER DISTRIBUTION OF PRIMARY AND SECONDARY FIBRES

	PRIMARY FIBRES	SECONDARY FIBRES
Mean (µm)	12.2	15.4
SD (µm)	2.0	1.3
CV (%)	16.4	8.6
Min (µm)	8.0	11.0
Max (µm)	18.0	19.0
Medullation (%)	nil	nil
Pigmented (%)		



Skin and fleece tests conducted by Dr. J.E. Watts M.V.Sc., Ph.D.

13 May 2008